

## IN THE CLAIMS

1. (Cancel) A flame retardant polyurethane composition produced by the process comprising of mixing and reacting the following components:

Component B consisting of

- (A). urea and/or urea condensates, in the amount of 50 to 200 parts by weight;
- (B). bio based compound selected from the group consisting of vegetable oils, molasses, corn syrup, sugar, lignin, sodium cellulose, hemi-cellulose and mixtures thereof in the amount of 50 to 200 parts by weight;
- (C) water, in the amount of 0 to 200 parts by weight;
- (D) blowing agent, in the amount of 0 to 50 parts by weight;
- (E) urethane catalyst, in the amount of 0 to 20 parts by weight;
- (F) carbonization auxiliaries, in the amount of 0 to 50 parts by weight;
- (G) filler, non-reactive, in the amount of 0 to 200 parts by weight based on weight;
- (H) surfactant, 0 to 20 parts by weight;
- (I) compound with an active hydrogen that will react with a polyisocyanate, in the amount of 0 to 100 parts by weight;

Component A consisting of:

- (J) polyisocyanate, in the amount of 50 to 400 parts by weight;

Component A and Component B are mixed and reacted.

2. (Cancel) The flame retardant composition of Claim 1 wherein the blowing agent is selected from the group consisting of methyl isobutyl ketone, acetone, mechanically frothed gas, methylene chloride and mixtures thereof.

3. (Cancel) The flame retardant composition of Claim 1 wherein the compound with an active hydrogen is a polyol.

4. (Cancel) The flame retardant composition of Claim 1 wherein the urethane catalyst is an amine and/or an organic metal catalyst.
5. (Cancel) The flame retardant composition of Claim 1 wherein the surfactant is a silicone surfactant.
6. (Cancel ) The flame retardant composition of Claim 1 wherein the carbonization auxiliaries are selected from the group consisting of phosphorus containing compounds, boron containing compounds, boron-phosphate containing compounds and sulfur containing compounds that produce acidic components in the pyrolysis mixture.
7. (Cancel) The flame retardant composition of Claim 1 wherein the filler is selected from the group consisting of urea, melamine, dicyandiamide, melamine cyanurate , amino phosphates, aminopolyphosphates, aminoplasts, phenoplasts, powdered synthetic resins, sawdust, carbohydrates, bituminous additives, graphite, graphite compounds, cyanuric derivatives or their formaldehyde resins, powdered coke, silica, fiberglass, alkali metal silicates, alkaline earth metal silicates, metals, metal silicates, oxides, carbonates, sulphates, phosphates and borates, glass beads, hollow glass beads, hydrated aluminum oxide and mixtures thereof.
8. (Cancel) A flame retardant polyurethane composition produced by the process comprising of mixing and reacting the following components:
  - Component B consisting of
    - (A) urea and/or urea condensate, in the amount of 50 to 200 parts by weight;
    - (B) bio based compound consisting of vegetable oil and is chosen from the group consisting of soy oil, rapeseed oil, palm oil, cotton seed oil, corn oil, safflower oil, flaxseed oil and mixture thereof;
    - (C) Water, in the amount of 0 to 200 parts by weight;

- (D) blowing agent, in the amount of 0 to 50 parts by weight;
- (E) urethane catalyst, in the amount of 0 to 20 parts by weight;
- (F) carbonization auxiliaries, in the amount of 0 to 50 parts by weight;
- (G) surfactant, 0 to 20 parts by weight;
- (H) compound with an active hydrogen that will react with a polyisocyanate, in the amount of 0 to 100 parts by weight;

Component A consisting of:

- (I) polyisocyanate, selected from the group consisting of ~~TDI, MDI, PMDI~~ 4,4'-diphenylmethane diisocyanate, 2,4-diphenylmethane diisocyanate and mixtures thereof in the amount of 50 to 400 parts by weight;

Component A and Component B are mixed and reacted.

9. (Currently amended) ~~—The flame-retardant urethane composition of Claim 1 wherein the —~~  
~~—bio-based compound is soy oil.—~~

~~A flame-retardant polyurethane composition produced by the process consisting of~~  
~~mixing and reacting the following components:~~

~~Component B consisting of~~

- ~~(A) urea and/or urea condensates, in the amount of 50 to 200 parts by weight;~~
- ~~(B) soy oil, in the amount of 50 to 200 parts by weight;~~
- ~~(C) water, in the amount of 0 to 200 parts by weight;~~
- ~~(D) blowing agent, in the amount of 0 to 50 parts by weight;~~
- ~~(E) urethane catalyst, in the amount of 0 to 20 parts by weight;~~
- ~~(F) carbonization auxiliaries, in the amount of 0 to 50 parts by weight;~~
- ~~(G) surfactant, 0 to 20 parts by weight;~~

(H) compound with an active hydrogen that will react with a polyisocyanate, in the amount of 0 to 100 parts by weight;

Component A consisting of:

(I) polyisocyanate, selected from the group consisting of 4,4 diphenylmethane diisocyanate, 2,4 diphenylmethane diisocyanate and mixtures thereof, in the amount of 50 to 400 parts by weight;

Component A and Component B are mixed and reacted.

10. (Approved) A flame retardant polyurethane composition produced by the process comprising of mixing and reacting the following components:

Component B consisting of

- (A): urea and/or urea condensates, in the amount of 50 to 200 parts by weight;
- (B) bio based compound selected from the group consisting of molasses, corn syrup, sugar and mixtures thereof.
- (C) water, in the amount of 0 to 200 parts by weight;
- (D) blowing agent, in the amount of 0 to 50 parts by weight;
- (E) urethane catalyst, in the amount of 0 to 20 parts by weight;
- (F) carbonization auxiliaries, in the amount of 0 to 50 parts by weight;
- (G) surfactant, 0 to 20 parts by weight;
- (H) compound with an active hydrogen that will react with a polyisocyanate, in the amount of 0 to 100 parts by weight;

Component A consisting of:

- (I) polyisocyanate, selected from the group consisting of 4,4 diphenylmethane diisocyanate, 2,4 diphenylmethane diisocyanate and mixtures thereof, in the amount of 50 to 400 parts by weight;

Component A and Component B are mixed and reacted.

11. (Cancel) The flame retardant urethane composition of Claim 1 wherein the polyisocyanate is selected from the group consisting of 4,4 phenylmethane diisocyanate, 2,4 diphenylmethane diisocyanate, and mixtures thereof.
12. (Cancel) The flame retardant composition of Claim 1 wherein the carbonization auxiliaries is a phosphorus containing compound.
13. (Cancel) The flame retardant composition of Claim 9 wherein the phosphorus containing compound is an organic phosphorus containing compound.
14. (Cancel) The flame retardant urethane composition of Claim 1 wherein the urea condensate is selected from a group consisting of biuret, cyanuric acid, cyanmelide, ammelide and mixtures of urea, biuret, ammelide and cyanuric acid.
15. (Cancel) The flame retardant composition of Claim 13 wherein the organic phosphorus compound is dimethyl methyl phosphonate.
16. (Cancel) A method for producing flame retardant urethane compositions consisting of mixing and reacting the following components;

Component B;

- (A) urea and/or urea condensate, in the amount of 50 to 200 parts by weight;
- (B) bio based compound selected from the group consisting of vegetable oils, molasses, corn syrup, sugar, lignin, sodium lignin sulfonate, sodium cellulose, hemi-cellulose and mixtures thereof in the amount of 50 to 200 parts by weight;
- (C) water, in the amount of 0 to 200 parts by weight;
- (D) blowing agent, in the amount of 0 to 50 parts by weight;
- (E) urethane catalyst, in the amount of 0 to 20 parts by weight;
- (F) carbonization auxiliaries; 0 to 50 parts by weight;

(H) surfactant, 0 to 20 parts by weight;

(I) compound with an active hydrogen that will react with a polyisocyanate, in the amount of 0 to 100 parts by weight;

Component A;

(J) polyisocyanate, in the amount of 50 to 400 parts by weight;

Component A and Component B are mixed and reacted.

17. (Cancel) The method of Claim 16 wherein the urea condensate is a mixture of urea, biuret, cyanuric and ammelide.

18. (Currently amended) ~~The method of Claim 16 wherein the bio-based compound is selected from the group consisting of vegetable oil, molasses, corn syrup, sugar and mixtures thereof.~~

A method for producing flame retardant urethane compositions

consisting of mixing and reacting the following components:

Component B consisting of:

(A) urea and/or urea condensate, in the amount of 50 to 200 parts by weight;

(B) bio based compound selected from the group consisting of vegetable oil, molasses, corn syrup, sugar and mixtures thereof, in the amount of 50 to 200 parts by weight,

(C) water, in the amount of 0 to 200 parts by weight;

(D) blowing agent, in the amount of 0 to 50 parts by weight;

(E) urethane catalyst, in the amount of 0 to 20 parts by weight;

(F) carbonization auxiliaries; 0 to 50 parts by weight;

(G) surfactant, 0 to 20 parts by weight;

(H) compound with an active hydrogen that will react with a polyisocyanate, in the

~~amount of 0 to 100 parts by weight:~~

~~Component A consisting of:~~

~~(i) polyisocyanate, selected from the group consisting of 4,4 diphenylmethane diisocyanate, 2,4 diphenylmethane diisocyanate and mixtures thereof, in the amount of 50 to 400 parts by weight:~~

~~Component A and Component B are mixed and reacted.~~

19. (Cancel) The method of Claim 16 wherein urea and/or urea condensate, bio based compound, water, blowing agent, urethane catalyst, carbonization auxiliaries, non-reactive filler, surfactant, compound with an active hydrogen that will react with a polyisocyanate are mixed then mixed and reacted with polyisocyanate selected from the group consisting of 4,4 diphenylmethane diisocyanate, 2,4 diphenylmethane diisocyanate and mixtures thereof.
20. (Cancel) A flame retardant polyurethane composition produced from reacting a polyurethane forming composition which comprises (A) a polyisocyanate and (B) a mixture of bio based compound selected from the group consisting of vegetable oil, molasses, corn syrup, sugar and mixture thereof, and urea and/or urea condensate, urethane catalyst, surfactant and water.

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**